



UNLIMITED CREATION

APPLICATION INSTRUCTIONS

FlexCut X Stretch

Very elastic, but still easy to cut and weed, stackable. 100% waterbased PU.

FEATURES:



**PU
water-
based**



60µ



**Cotton, polyester,
blended fabrics..**
Also suitable for many
water repellent coated textiles.



60°C

CUTTING CONDITIONS:



**Blade
30 - 45°**



**low/
medium**



30 - 40 cm/s

TRANSFER CONDITIONS:



165 °C



17 s




**medium/
high**




Hot peel

Flex on Flex possible



1. Cut mirrored



2. Weed design



3. Transfer design



4. Remove liner, done !

► PACKAGING



50 cm 25 m

50 cm 10 m

50 cm 5 m

Store in a cool and dry place; protect against the influence of light when stored. We recommend not to exceed a storage period of 18 months. The technical specifications rest on extensive tests and technical research. Due to the variety of possible influences during refinement, and use, the specifications should be viewed as reference values. We recommend a suitability test on the original material. A legally binding warranty of specific characteristics cannot be derived from our specifications.

S E F • 110 BD DENIS-PAPIN 53000 LAVAL – FRANCE
TEL. +33 2. 43 53 36 48 FAX +33 2. 43 67 11 78
www.seftextile.com E-mail: contact@sef-france.com
SAS. CAPITAL € 945 000 RCS, LAVAL 304.802.291.00027





UNLIMITED CREATION

AVAILABLE COLORS



WHITE 01



PACIFIC BLUE 19
P 647 C



GREY 15
P 430 C



SILVER METALLIC 31
P 877 C




LEMON YELLOW 05
P 012 C



ROYAL BLUE 21
P 280 C



DARK GREY 16
P COOL GRAY 11 C



GOLD METALLIC 32
P 871 C



SUNNY YELLOW 06
P 116 C



NAVY BLUE 22
P 289 C



BLACK 02
P PROCESS BLACK C



ORANGE 07
P 021 C



GREEN 25
P 341 C



PASSION RED 33
P 185 C



ELECTRIC RED 12
P 1797 C

Store in a cool and dry place; protect against the influence of light when stored. We recommend not to exceed a storage period of 18 months. The technical specifications rest on extensive tests and technical research. Due to the variety of possible influences during refinement, and use, the specifications should be viewed as reference values. We recommend a suitability test on the original material. A legally binding warranty of specific characteristics cannot be derived from our specifications.

